



*solid solutions to better hardscapes*

---

PO Box 70 • 32020 126<sup>th</sup> St • Princeton, MN 55371 • Tel 800-752-9326 • Fax 763-389-2725

---

## SRW EC8

SRW Products Manufactures/Supplies a 100% Polypropylene Non-Woven produced by needle punching staple fibers in a random network to form a high strength dimensionally stable fabric. The polypropylene material is specially formulated to resist ultraviolet light deterioration, and is inert to commonly encountered soil chemicals. The fabric will not rot or mildew, is non-biodegradable, and is resistant to damage from insects and rodents. This fabric is **MADE IN THE USA**.

SRW EC8 meets or exceeds the physical property values listed below.

Fabric Property	Test Method	Units	Minimum Average Roll Value
<b>Grab Tensile</b>	ASTM D 4632	lbs.	205(.911 kN)
<b>Grab Elongation</b>	ASTM D 4632	%	50
<b>CBR Puncture</b>	ASTM D-6241	lbs.	525(2.33 kN)
<b>Trap-Tear Strength</b>	ASTM D 4533	lbs	80(.356 kN)
<b>Mullen Burst Strength</b>	ASTM D 3786	psi	400
<b>Puncture</b>	ASTM D 4833	lbs.	130
<b>Permittivity</b>	ASTM D 4491	sec <sup>-1</sup>	1.4
<b>Water Flow</b>	ASTM D 4491	gpm/ft <sup>2</sup>	90(3657 l/min/sm)
<b>UV Resistance</b>	ASTM D 4355	%	80
<b>AOS</b>	ASTM D 4751	US Sieve	#80(.180 mm)

Values Provided represent expected values at time of manufacture. This document provides the characteristic properties of the product described. Product packaging will clearly state one of these numbers, verifying that it is EC8 inside. **EC8 or RO80**.